

If No. 561 Zinc Filler is to be added, the Filler must be kept absolutely dry and at a temperature of 60-80°F. Slowly add 5 lbs. of Zinc Filler to each gallon of No. 560. Care must be taken to avoid entrapping air which will contain moisture. The Zinc will rapidly settle out if not kept continually agitated at slow speeds.

Do not use plastic tools or implements to weigh, handle, or clean up No. 561 as static charges may cause an explosion..

COVERAGE

866 ft² per gallon @ 1 mil dry film thickness.

320 ft² per gallon @ 5 mils wet film thickness

533 ft² per gallon @ 3 mils wet film thickness

SETTING/CURING

Hi-Temp Primer No. 560 will dry to the touch in approximately 1-2 hours at 70°F. Topcoating should occur no sooner than six hours after application. Hi-Temp Primer No.560 may be topcoated after six hours at 70°. If the duration before topcoating exceeds 18 hours, consult Sauereisen to discuss proper solvent-wipe and sanding procedures.

PACKAGING

Hi-Temp Primer No. 560 is packaged in a one gallon can. Material weight is approximately 8.5 pounds per gallon.

CLEAN-UP

All equipment should be cleaned by scrubbing with a stiff brush and MEK at the end of each working period or when build-up becomes pronounced.

SHELF LIFE

Sauereisen Hi-Temp Primer No. 560 has a shelf life of six (6) months when stored in unopened, tightly sealed containers in a dry location at 70°F. If there is a doubt as to the quality of the materials, consult a Sauereisen representative.

CAUTION

Consult Material Safety Data Sheets and container label Caution Statements for hazards in handling these materials.

WARRANTY

We warrant that our goods will conform to the description contained in the order, and that we have good title to all goods sold. WE GIVE NO WARRANTY, WHETHER OF MERCHANTABILITY, FITNESS FOR PURPOSE OR OTHERWISE, EXPRESS OR IMPLIED, OTHER THAN AS EXPRESSLY SET FORTH HEREIN. We are glad to offer suggestions or to refer you to customers using Sauereisen cements and compounds for a similar application. Users shall determine the suitability of the product for intended application before using, and users assume all risk and liability whatsoever in connection therewith regardless of any suggestions as to application or construction. In no event shall we be liable hereunder or otherwise for incidental or consequential damages. Our liability and your exclusive remedy hereunder or otherwise, in law or in equity, shall be expressly limited to our replacement of non-conforming goods at our factory or, at our sole option, to repayment of the purchase price of non-conforming goods.

Sauereisen®, SewerGuard®, ConoCrete™, RestoKrete®, ConoGlaze™, and FibreCrete™ are all products or services denoted with ™ or ®. These are trademarks or registered trademarks of Sauereisen, Inc. Sauereisen trademarks may not be used in conjunction with any product or service that is not a Sauereisen product or service.

SAUEREISEN ...since 1899

160 Gamma Drive
Pittsburgh, PA 15238-2989 U.S.A.
Phone 412.963.0303 Fax 412.963.7620
www.sauereisen.com